


MALZEME TEST RAPORU

Numune Adı	Deneme	Rapor Tarihi	15.05.2020 14:49
Numune Cinsi	Plastik	Test Tarihi	15.05.2020 11:52
Operatör	Yönetici	Kalınlık	3 mm
Test İd	67	b	6 mm



No	Renk	Tarih	Max kuvvet N	Max kuvvet uzaması %	Gerilme Mpa	Kopma kuvveti N	Kopma uzaması %	Test süresi sn
1	Red	15.05.2020 11:24	229.1	29.783	12.726	229.1	29.783	7.11
2	Blue	15.05.2020 11:24	232.6	29.412	12.922	232.6	29.412	6.99
3	Green	15.05.2020 11:24	222.9	29.308	12.381	222.9	29.308	6.98
4	Orange	15.05.2020 11:25	219.1	29.313	12.170	219.1	29.313	6.94
5	Yellow	15.05.2020 11:25	203.9	28.825	11.329	203.9	28.825	7.03
6	Cyan	15.05.2020 11:26	200.9	27.325	11.161	200.9	27.325	6.65
7	Magenta	15.05.2020 11:26	224.1	28.645	12.448	224.1	28.645	6.80
8	Red-Orange	15.05.2020 11:26	216.8	28.692	12.043	216.8	28.692	7.31
9	Grey	15.05.2020 11:27	208.5	27.706	11.581	208.5	27.706	6.64
10	Green	15.05.2020 11:27	212.1	28.462	11.781	212.1	28.462	6.64
11	Red	15.05.2020 11:28	201.2	27.231	11.179	201.2	27.231	6.66
12	Orange	15.05.2020 11:28	226.2	28.403	12.564	226.2	28.403	6.82
13	Olive	15.05.2020 11:28	201.2	27.041	11.178	201.2	27.041	6.59
14	Cyan	15.05.2020 11:29	200.3	27.385	11.128	200.3	27.385	6.69

No	Renk	Tarih	Max kuvvet N	Max kuvvet uzaması %	Gerilme Mpa	Kopma kuvveti N	Kopma uzaması %	Test süresi sn
15	■	15.05.2020 11:29	227.3	27.769	12.628	227.3	27.769	6.60
16	■	15.05.2020 11:29	227.2	27.929	12.624	227.2	27.929	6.61
17	■	15.05.2020 11:52	204.8	14.743	11.380	204.8	14.743	3.51
18	■	15.05.2020 11:52	246.9	15.919	13.716	246.9	15.919	3.74
19	■	15.05.2020 11:52	248.0	15.987	13.776	248.0	15.987	3.79
20	■	15.05.2020 11:52	204.8	14.704	11.378	204.8	14.704	3.65
		Ortalama	217.9	25.729	12.105	217.9	25.729	6.19
		St.Sapma	14.9	5.393	0.827	14.9	5.393	1.31
		En Büyük	248.0	29.783	13.776	248.0	29.783	7.31
		En Küçük	200.3	14.704	11.128	200.3	14.704	3.51